



PUTOP PU METALLIC

DESCRIPTION	High-quality water-borne metal effect lacquer for indoor use of a modified polyurethane.
FEATURES	Unique metallic shine. Scratch and scrub-resistant. Hand grease resistance. Bright colors and excellent hide. Solvent-free and low odor. Quick drying, multiple layers to apply in one day. Easy to process.
APPLICATION	Suitable for processing on various surfaces such as wood, metal, plastic and such.
COLORS	235 (see Neverlak 8000 color palette).
GLOSS LEVEL	Satin gloss.
PACKAGING	1 and 2,5 liter.
BASIC DETAILS	Drying time determined at 23°C and 50% relative humidity. Density : 1.1 kg / dm ³ . To Touch : approximately 1 hour. Dry : approximately 2 hours. To Recoat : approximately 4 hours. To Full Cure : after 14 days. Pot life : at least 12 months in closed original packaging. Keep in a cool, dry and frost-free place. V.O.C. : class A / I. 200 g / l. (2010) max. 60 g / l.
COVERAGE	Approximately 10 sq. meters per liter on smooth, nonporous surfaces depending on the method of processing and the nature and structure of the substrate.
PROCESSING	Processing method sprayer : preferably process with a paint sprayer. : Air sprayer; spray pressure: 2-4 bar. nozzle opening: 1.5-2 mm. : HVLP air sprayer; spray pressure: 3-4 bar. nozzle opening: 1.8 mm

: Airmix;
spray pressure airless pump:
from 50 bar.
compressor pressure: 3-4 bar.
tip: 4/13.

Processing method brush or roller : stir well before use.
: processing with brush or roller
(nylon) is possible. Due to the
metallic effect and gloss level,
visible overlaps will be seen
sooner.
When processing with a roll,
always roll in one direction.

Processing condition : apply when air, product and
surface temperatures are
between 5°C and 28°C.
: relative air humidity max 85%.
: ensure good ventilation.

Dilution : water, preferably use undiluted.

SUBSTRATE TREATMENT

The surface must be clean, dry, and free of grease and any
other surface contaminants.
Impregnate porous surfaces with Putop Impregnate.
After possible impregnation, pre-treat the surface with
Putop Supreme. Pre-treat difficult to adhere surfaces with
NovaShield Primer.

CLEANING TOOLS

Immediately after use with water.

TECHNICAL ADVICE

For advice, please contact:
Neverlak B.V. T : 0031 (0) 20 6655 678
E : info@neverlak.nl

The information mentioned above is entirely without obligation and is based on your own observations and experiences. Our information counts as non-committal advice and does not release the customer / processor from the obligation to test the products supplied by us before proceeding to the processing process. The application and processing of our products takes place outside of our control capabilities and observation and therefore solely for the responsibility of the buyer / processor.

Upon the publication of a new edition of this Technical Data Sheet, this publication loses its validity.